



# ULTRA GRAB CRYSTAL

UNIVERSAL POLYMER BASED CRYSTAL CLEAR ASSEMBLY ADHESIVE WITH FAST FINAL STRENGTH BUILD-UP



- Good filling capacity
- Resistant to temperatures between -40 °C and +100 °C
- Water and all-weatherproof
- 100 % adhesive (non-shrinking)
- Also bonds to slightly damp surfaces
- Solvent-free
- Excellent bonding without primer
- Acid-free, odourless

## CERTIFICATES & STANDARDS

Certificates	
	TÜV: Approved and certified by TÜV Rheinland on shear strength, tensile strength, elasticity and adhesion to different materials. Certificate TÜV 43168.
	EMICODE: Classification system (GEV) of emission properties for construction products in indoor areas. EC-1 Plus (Very low emission Plus)

## PRODUCT DESCRIPTION

Universal, crystal clear assembly adhesive based on unique STP technology, with fast final strength building. For bonding and fixing almost all (construction) materials on almost all surfaces (both smooth, porous and non-porous surfaces). Extra strong. Crystal clear. Super fast.

## FIELD OF APPLICATION

Ideal for assembling all kinds of (building) materials, such as wood, stone, concrete, metal, many synthetics, gypsum and polystyrene foam onto (porous), Trespa®, surfaces such as concrete, stone, plasterwork, wood and chipboard. Very suitable for attaching, e.g., timber framework, skirting boards, doorsteps, window sills, construction boards, paneling, laths, wood strips, ducts, name plates, house numbers, wall covering sheets, panels, thresholds, ceramic tiles, sockets and electrical boxes. Also very suitable for decoration materials, such as ornaments and decorative edgings in plaster/polystyrene/polyurethane, name plates, suspension hooks. Also extremely suitable for surface bonding.

Not suitable for PE, PP, PTFE and bitumen. When gluing plastics always perform an adhesion test first. Adhesion to plastics can vary depending on the type of synthetic and the quality of the plastic.

## PROPERTIES

- Crystal clear
- Very high final bond strength
- Super-fast building of final bonding strength
- Permanently elastic
- Can be used internally and externally
- Paintable (test first)

## PREPARATION

**Working Conditions:** Only apply at temperatures between +5 °C and +40 °C.

**Surface Requirements:** Both parts must be solid, clean, free of dust and grease. Use of primer not required. The surface may be slightly moist.

**Tools:** Apply cartridge contents using a sealant gun. If necessary, use a rubber mallet to tap lightly.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# ULTRA GRAB CRYSTAL

**UNIVERSAL POLYMER BASED CRYSTAL CLEAR ASSEMBLY ADHESIVE WITH FAST FINAL STRENGTH BUILD-UP**

## APPLICATION

**Coverage:** With spot bonding: 5-8 m<sup>2</sup>/kg. Stripes: one cartridge issues approx. 8-15 metres of adhesive (depending on the diameter of the cut nozzle).

### Directions for use:

Before using open cartridge at the top by cutting off the plastic nipple above the thread with a sharp knife. Fix the nozzle onto the cartridge and cut at an angle to the desired diameter.

Apply in stripes or dots (every 10 - 40 cm). Always apply to the corners and along the edges of construction boards.

Correctly position material within 10 minutes and press firmly or lightly tap with a rubber mallet. If necessary, clamp or fixate heavy materials for 4 hours. Can be handled after 2 hours (the connection is now strong enough to withstand transportation or a light load), maximum final strength after approx. 4 hours, depending on the surface and the ambient conditions.

**Stains/residue:** Use white spirit for cleaning tools and removing wet adhesive residue. Dry adhesive residue can only be removed mechanically.

**Points of attention:** The following drying times are based on bonding at least one porous material and an adhesive layer of approx. 1 mm thickness. If two non-porous materials are being bonded and/or the layer of adhesive is thicker, the drying times may be substantially longer. When adhesive is applied underwater, it may turn white. Avoid lasting direct contact with UV radiation (eg. applications outdoors).

## TECHNICAL SPECIFICATIONS

100% modulus:	0.9 MPa
Chemical base:	SMP Polymer
Chemicals resistance:	Good
Cure rate:	2.5 mm/24h
Density approx.:	1.04 g/cm <sup>3</sup>
Elasticity:	Good
Elongation of rupture:	250 %
Filling capacity:	Very good
Final bond strength:	250 N/cm <sup>2</sup>
Final bond strength after:	4 hours. This might vary, based on circumstances, like materials, temperature and humidity.
Hardness (Shore A):	42
Initial Bonding after:	2 hours. This might vary, based on circumstances, like materials, temperature and humidity.
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	100 °C
Mildew resistance:	Good
Moisture resistance:	Very good
Paintability:	Good
Shear strength:	250 N/cm <sup>2</sup>
Skinover time:	30-45 minutes
Solid matter approx.:	100 %
Solvent free:	Yes
Tensile strength (N/cm <sup>2</sup> ) approx.:	150 N/cm <sup>2</sup>
UV resistance:	Moderate
Viscosity:	Pasty
Water resistance:	Good
Colour:	Crystal clear

## STORAGE CONDITIONS

Close container properly and store in a dry, cool and frost-free place.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.